



## Physical Properties and General Processing Conditions

### Z-26060 MB PE Standard White Masterbatch Polyethylene (LLDPE) White

Z-26060 MB PE Standard White is a superior-quality extended white masterbatch. It contains a finely dispersed combination of a premium Rutile Titanium Dioxide and a high quality extender to provide excellent opacity. It is suitable for LDPE, LLDPE, and HDPE in blown and cast film, sheet extrusion, injection and blow molded applications.

PHYSICAL PROPERTIES & AVERAGE VALUES	ENGLISH	SI METRIC	TEST
Polyethylene Carrier (LLDPE)	30 %	30 %	
Rutile Titanium Dioxide	~ 45 %	~ 45 %	
Total Inorganic Content	70 %	70 %	
Specific Gravity	1.8	1.8	D 792
Melt Flow Rate	20 g/10 min	20 g/10 min	D 1238
Bulk Density	113 g/100 cc	113 g /100 cc	
Pellet Size	30 pellets/g	30 pellets/g	
Moisture Content	0.05%	0.05%	
Packaging	Gaylord, drum, or bag	Gaylord, drum, or bag	

#### PROPERTY NOTES

- Data herein is typical and not to be construed as specifications.
- No dispersion aids, waxes or stearates are used in this product.
- Z-26060 MB PE Standard White maybe used to meet the requirements of Title 21 of the U.S. Federal Code of Regulations (FDA). Contact your RTP Color sales specialist should you require more information regarding the use of Z-26060 MB PE Standard White in food contact applications.
- Z-26060 MB PE Standard White meets the Coalition of Northeastern Governors (CONEG) requirements of a total of less than 100 PPM contamination by lead, mercury, cadmium, and hexavalent chromium.
- Z-26060 MB PE Standard White is not known to contain chemicals listed in the California Safe Drinking Water and Toxic Enforcement Act of 1996 (Proposition 65).
- Z-26060 MB PE Standard White contains no animal based ingredients and its use will not affect the kosher stats of finished products.

GENERAL PROCESSING CONDITIONS	ENGLISH	SI METRIC
Injection Pressure	10000-15000 psi	69-103 MPa
Melt Temperature	380-450 °F	193-232 °C
Mold Temperature	70-150 °F	21-66 °C
Drying	2 hr @ 175 °F	2 hr @ 79 °C

#### PROCESSING NOTES

- None

19 MAY 2005

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics for injection molding. Because injection mold design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.