



Product Data Sheet & General Processing Conditions

EMI 330 E FR
Polycarbonate (PC)
Stainless Steel Fiber
Electrically Conductive
EMI/RFI Shielding
Flame Retardant



PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	10 %	10 %	
Specific Gravity	1.40	1.40	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0040 - 0.0070 in/in	0.40 - 0.70 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	14.0 ft-lbs/in	747 J/m	D 4812
Tensile Strength	9600 psi	66 MPa	D 638
Tensile Elongation	4.0 - 6.0 %	4.0 - 6.0 %	D 638
Tensile Modulus	0.45 x 10 ⁶ psi	3103 MPa	D 638
Flexural Strength	16500 psi	114 MPa	D 790
Flexural Modulus	0.45 x 10 ⁶ psi	3103 MPa	D 790

ELECTRICAL

Volume Resistivity	< 1E1 ohm.cm	< 1E1 ohm.cm	D 257
Surface Resistivity	< 1E6 ohm/sq	< 1E6 ohm/sq	D 257
Surface Resistance	< 1E5 ohm	< 1E5 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 0.50 s	< 0.50 s	FTMS101C 4046.1

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	269 °F	132 °C	D 648
Ignition Resistance* Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94

EMI

Shielding Effectiveness @ 2 mm thickness	37 dB @ 300 MHz	37 dB @ 300 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	37 dB @ 500 MHz	37 dB @ 500 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	38 dB @ 700 MHz	38 dB @ 700 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	40 dB @ 1000 MHz	40 dB @ 1000 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	44 dB @ 1300 MHz	44 dB @ 1300 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	46 dB @ 1500 MHz	46 dB @ 1500 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	46 dB @ 300 MHz	46 dB @ 300 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	45 dB @ 500 MHz	45 dB @ 500 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	48 dB @ 700 MHz	48 dB @ 700 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	53 dB @ 1000 MHz	53 dB @ 1000 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	53 dB @ 1300 MHz	53 dB @ 1300 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	55 dB @ 1500 MHz	55 dB @ 1500 MHz	D 4935

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	530 - 580 °F	277 - 304 °C
Mold Temperature	160 - 250 °F	71 - 121 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Use a reverse barrel profile. Remove hopper magnets. Allow 4 - 5 shots to properly disperse the conductive fibers. The surface finish should have a silver streaking appearance, not clumps.

Remove hopper magnets.

Desiccant Type Dryer Required.

4 Mar 2021 EDL

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein.

Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.

RTP COMPANY • 580 EAST FRONT STREET • WINONA, MN 55987 • 507-454-6900