



## Product Data Sheet & General Processing Conditions

**RTP 800 AR 10 TFE 15**  
**Acetal (POM)**  
**Aramid Fiber**  
**PTFE Lubricated**

### PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

| PERMANENCE                                   | English               | SI Metric     | ASTM TEST |
|--|-----------------------|---------------|-----------|
| Primary Additive                             | 10 %                  | 10 %          |           |
| Specific Gravity                             | 1.49                  | 1.49          | D 792     |
| Molding Shrinkage<br>1/8 in (3.2 mm) section | 0.0100 - 0.0200 in/in | 1.00 - 2.00 % | D 955     |

### MECHANICAL

|  |                            |             |        |
|--|----------------------------|-------------|--------|
| Impact Strength, Izod<br>notched 1/8 in (3.2 mm) section | 1.2 ft-lbs/in              | 64 J/m      | D 256  |
| unnotched 1/8 in (3.2 mm) section                        | 9.0 ft-lbs/in              | 481 J/m     | D 4812 |
| Tensile Strength   | 8000 psi                   | 55 MPa      | D 638  |
| Tensile Elongation                                       | 5.0 - 8.0 %                | 5.0 - 8.0 % | D 638  |
| Tensile Modulus  | 0.45 x 10 <sup>6</sup> psi | 3103 MPa    | D 638  |
| Flexural Strength  | 11500 psi                  | 79 MPa      | D 790  |
| Flexural Modulus   | 0.40 x 10 <sup>6</sup> psi | 2758 MPa    | D 790  |

### ELECTRICAL

|                    |                    |                    |       |
|--------------------|--------------------|--------------------|-------|
| Volume Resistivity | 1E14 - 1E16 ohm.cm | 1E14 - 1E16 ohm.cm | D 257 |
|--------------------|--------------------|--------------------|-------|

### THERMAL

|  |              |             |       |
|--|--------------|-------------|-------|
| Deflection Temperature<br>@ 264 psi (1820 kPa) | 220 °F       | 104 °C      | D 648 |
| Ignition Resistance*<br>Flammability**         | HB @ 1/16 in | HB @ 1.5 mm | D 635 |

### PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

### GENERAL PROCESSING FOR INJECTION MOLDING

|                    | English           | SI Metric      |
|--------------------|-------------------|----------------|
| Injection Pressure | 10000 - 15000 psi | 69 - 103 MPa   |
| Melt Temperature   | 360 - 425 °F      | 182 - 218 °C   |
| Mold Temperature   | 175 - 225 °F      | 79 - 107 °C    |
| Drying             | 2 hrs @ 250 °F    | 2 hrs @ 121 °C |
| Moisture Content   | 0.15 %            | 0.15 %         |
| Dew Point          | -25 °F            | -32 °C         |

### PROCESSING NOTES

Desiccant Type Dryer Required.

30 Apr 2021 TES

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.

RTP COMPANY • 580 EAST FRONT STREET • WINONA, MN 55987 • 507-454-6900