



Product Data Sheet & General Processing Conditions

RTPrene™ K 87 BK Thermoplastic Vulcanizate (TPV) UV Stabilized Preliminary Datasheet

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.96	0.96	D 792
MECHANICAL			
Tensile Strength Die C, 0.080 in, 20 in/min (2.0 mm, 500 mm/min)	2654 psi	18.3 MPa	D 412
Tensile Elongation Die C, 0.080 in, 20 in/min (2.0 mm, 500 mm/min)	570.0 %	570.0 %	D 412
Tensile Stress Die C 0.080 in, 20 in/min (2.0 mm, 500 mm/min) @ 100 %	1232.8 psi	8.5 MPa	D 412
Tear Strength, Die C	350.3 pli	61.3 N/mm	D 624
Compression Set 22h @ 70 °C (158 °F), Method B, Type 2	47 %	47 %	D 395
Hardness Shore A, 15 s delay	94	94	D 2240

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Melt Temperature	400 - 450 °F	204 - 232 °C
Mold Temperature	50 - 125 °F	10 - 52 °C
Drying	2 - 4 hrs @ 180 °F	2 - 4 hrs @ 82 °C
Moisture Content	< 0.05 %	< 0.05 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Sept 20, 23 SAC

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.