



Product Description

ACX 111257 Polypropylene (PP) Anti-Stat Masterbatch 20% Active

INTRODUCTION

Polyolefins are inherently hydrophobic allowing the build-up of static charge. Excessive static causes processing problems during manufacturing and handling. This build-up also creates dust accumulation problems in end use applications.

ACX 111257 is a 20% glycerol monostearates (GMS) masterbatch that improves anti-static properties and dust accumulation issues with polypropylene.

BENEFITS

- ACX 111257 is provided in masterbatch form to facilitate handling and processing.
- GMS chemistry provides anti-static properties.
- Good performance in low humidity environments.
- Less corrosive compared to traditional Amine chemistry.

RECOMMENDED USAGE

Typical use levels range from 0.5% to 2% depending on application, part thickness, desired anti-static performance and duration of properties. This product is supplied in a granular form.

The optimum additive loading in the finished part depends on the specific processing conditions and environment the part is to be used in. Processors will need to confirm the optimum loading level for each particular end use.

STORAGE AND HANDLING

ACX 111257 is highly hydrophilic, and readily absorbs moisture. It should be stored in closed containers in a cool and dry environment to prevent water absorption.

05 DEC 2016

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics for injection molding. Because injection mold design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.